

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61C 8/00, A61L 27/00	A1	(11) International Publication Number: WO 98/51231 (43) International Publication Date: 19 November 1998 (19.11.98)
(21) International Application Number: PCT/SE98/00891 (22) International Filing Date: 14 May 1998 (14.05.98) (30) Priority Data: 9701872-5 16 May 1997 (16.05.97) SE (71) Applicant (for all designated States except US): NOBEL BIOCARE AB [SE/SE]; P.O. Box 5190, S-402 26 Göteborg (SE). (72) Inventors; and (75) Inventors/Applicants (for US only): LARSSON, Cecilia [SE/SE]; Aschebergsgatan 9, S-411 27 Göteborg (SE). THOMSEN, Peter [SE/SE]; Hängestensvägen 2, S-421 67 Göteborg (SE). (74) Agent: OLSSON, Gunnar; Nobel Biocare AB, P.O. Box 5190, S-402 26 Göteborg (SE).		(81) Designated States: AU, CA, JP, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>In English translation (filed in Swedish).</i>
(54) Title: AN IMPLANT ELEMENT (57) Abstract An implant element for permanent anchorage in bone tissue in which at least the surface is intended to face the tissue in the implantation region. The element is made of titanium with a titanium oxide surface which has been modified by anodization to acquire an oxide thickness of approximately 10-200 nm. Also acquired are an increased surface oxide crystallinity and a roughness on the submicrometer scale in order to provide a high degree of bone-to-implant contact.		

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		

An implant element

Oral implants are made of syntetic materials and inserted in mucosal soft tissues and bone to serve as anchorage for prosthetic constructions. The choice of materials for bone anchorage has been discussed and considered over the years (reviewed in (Brånemark, 1996)). Osseointegrated titanium implants ad modum Brånemark have been successfully used for 30 years. There are several factors which are assumed to play important roles for the outcome of this treatment, for instance the choice of titanium with its adequate mechanical properties and corrosion resistance (Williams, 1981), surface topography and the relatively non-traumatic surgical procedures.

It is assumed that two-stage surgical procedure with an early post-operative period (3-6 months) without loading is important for the initial implant stability during the early healing phase. However, the two-stage surgical technique may be a disadvantage for the patient and requires more resources. In clinical practice, not only the materials and surgical procedures but also systemic and local host factors set the limits for treatment. It has been found that the failure rates are higher in the maxilla and the posterior mandible and that the success rates very much depend on the quality of bone (Esposito et al., 1997). It is therefore of importance to identify the beneficial and negative factors related both to the implant and the host in order to optimize the implant treatment. A reduction of the healing period and a maintenance of long-term stability during clinical loading conditions therefore appears essential.

A biomaterial is a material used in a medical device, intended to interact with biological systems (Black, 1992). The materials used in man-made structures may be divided into three classes: metals, ceramics and polymers. The

classes are distinguished by the type of interatomic bonding (Cooke et al., 1996).

Metals consist of a large number of small crystallites. Each crystallite is an aggregate of atoms regularly
5 arranged in a crystalline structure. When molten metals (which are amorphous) solidify small crystals (grains) start to grow. The irregularly arranged crystals eventually meet each other which gives rise to boundaries between the crystals, grain boundaries. The imperfect packing of atoms
10 in the boundaries constitutes weak points in the material, which will be most strongly affected by a surface treatment such as etching or plasma cleaning and a groove will be created showing up as a darker line. The surface properties of a material is different from the bulk properties.

15 The term commercially pure (CP) titanium is applied to unalloyed titanium and includes several grades containing minor amounts of impurity elements, such as carbon, iron and oxygen. The amount of oxygen can be controlled at different levels to provide increased strength. There are
20 four grades of titanium where grade 1 (used in the present thesis) contains the lowest amount of oxygen. The microstructure of CP titanium is essentially all α titanium which has a HCP crystal structure.

Titanium dioxide, TiO_2 , is the most common and stable of
25 the titanium oxides, while Ti_2O_3 and TiO are more rare (Lausmaa, 1991).

TiO_2 can exist in three crystalline modifications; anatase (tetragonal structure), rutile (tetragonal), and brookite (orthorhombic). Rutile and anatase are the most usual forms
30 whereas brookite is very rare (Keesman, 1966).

Techniques have been developed to alter and modify the surface properties of implants via mechanical and chemical procedures (Lausmaa, 1996; Smith et al., 1991a; Smith et

al., 1991b). Plasma-spraying, sputter deposition, oxidation, vaporization, (grit, sand) blasting, grinding, etching, plasma cleaning and ion bombardment are examples of techniques available for this purpose.

- 5 Electropolishing is an electrochemical technique often used to obtain an improved surface finish by controlled dissolution of the surface layer of the metal. The amorphous surface layer produced by the machining of the implants is removed. After electropolishing a
10 polycrystalline surface with a surface oxide consisting mainly of TiO_2 , typically 3-5 nm thick as measured by X-ray photoelectron spectroscopy (XPS), is found on the surface (Lausmaa, 1996).

Anodic oxidation is an electrochemical method used to
15 increase the thickness of the oxide layer on metal implants. A current is applied in an electrolytic cell in which the sample is the anode. When a potential is applied on the sample, the current will transport oxygen containing anions through the electrolyte and a continuous oxide is
20 formed on the metal sample. The stoichiometry of anodic oxides on titanium is mostly TiO_2 . The anodic oxides on titanium contain various structural features such as porosity (Lausmaa, 1996).

In order to characterize the surface properties after the
25 modifications the following techniques were used; SEM and AFM for surface topography and roughness; ESCA and AES for surface composition and oxide thickness.

Interactions between titanium surfaces and proteins/cells/tissues

- 30 A review of the literature shows that surface modifications influence the biological response. The first events that take place when an implant is inserted in vivo is the exposure of the material surface to water and biomolecules,

including plasma proteins. Both under *in vitro* and *in vivo* conditions serum proteins are known to adsorb to foreign material surfaces within seconds. The adsorption and desorption phenomena on different biomaterial surfaces have been studied intensely. A working hypothesis is that the biological response is directed by the initial protein adsorption which subsequently influence the cellular/tissue response and ultimately the performance of the implant (Horbett, 1996).

10 Three types of adsorption/desorption patterns have been described for metals and their oxides (Williams and Williams, 1988). For example, titanium was found to adsorb low levels of albumin, which remained low during a 48 h period. In addition, the albumin desorbed relatively easily. Other metal surfaces such as vanadium, showed an initially low amount of albumin, but the amount increased and desorption was slow. Gold was found to be characteristic for a surface with a high initial adsorption of albumin and the amount increased throughout the experiment.

15
20

A modification and variation on surface properties and the resulting effects on molecular adsorption to surfaces may provide important insights into the role of surface properties for biological reactions. Modified and characterized surfaces have been used to detect differences in the behaviour and adsorption patterns of proteins (McAlearney et al., 1991; McAlearney et al., 1996; Nygren, 1996; Shelton et al., 1988; Sunny and Sharma, 1990; Tengvall et al., 1992; Wälivaara et al., 1994; Wälivaara et al., 1992). Shelton et al (1988) found that a larger amount of proteins were adsorbed to negatively charged polymer beads than to positively charged beads but the roughness of the surface did not seem to influence protein adsorption or cellular behaviour. In general, rough surfaces are

25
30

considered more wettable than smooth surfaces which may be an effect caused by an increase of the surface area as well as by an increased hydrophilicity of the surface (Curtis et al., 1983).

5 Nygren (1996) found two different reactions when hydrophilic and hydrophobic titanium surfaces were exposed to whole blood. On the hydrophobic surface, adherent platelets and fibrinogen were present while complement factor 1 (C1) and prothrombin/thrombin were present on the
10 hydrophilic surface. Baier et al. (1982) has reviewed the principles of adhesive phenomena in diverse systems and he pointed out the wettability of a surface as the important parameter influencing the protein adsorption pattern.

The surface energy of a material is influenced by various
15 cleaning procedures and the oxide thickness. According to Sunny and Sharma (1990) an increase of the oxide layer on aluminium, increased the hydrophobicity of the surface, resulting in an increased adsorption of fibrinogen. In addition, the glow discharge technique rendered the surface
20 more hydrophilic causing less fibrinogen adsorption. However, other results were obtained by Wälivaara et al (1994) who found that the titanium oxide thickness and carbon contamination had no influence on protein adsorption and contact activation. Interestingly, increased surface
25 concentrations of complement factor 3 (C3) was correlated with an increasing titanium dioxide film thickness and/or crystallinity. The oxide crystallinity seemed to be of more significance than the oxide thickness (McAlarney et al., 1996). In another study, McAlarney (1991) found that C3
30 adsorbed preferentially onto grain boundaries which may be explained by the differences in surface energy between grain boundaries and bulk surface. It is known that titanium oxide surfaces bind cations, particularly polyvalent cations (Abe, 1982).

The oxide layer is highly polar and attracts water and water-soluble molecules. In general therefore, calcium ions may be attracted to the oxide surface by electrostatic interaction with oxygen (O^-). In a study by Lausmaa et al
5 (1988), approximately 100 samples prepared according to clinical procedures were analyzed with ESCA. The spectra showed that the surface consisted mainly of TiO_2 . Carbon and smaller amounts of N, Cl, Ca, S, P, Na and Si were found on the surface but after sputtering all were removed
10 except for Ca which was found throughout the oxide.

It is of a major interest to understand, on a time-scale from immediate responses to years, how material properties influence cellular activity in the interface and vice versa since rejection, excessive scar formation/encapsulation by
15 fibrous tissue and restitution of original tissue may largely influence the performance of the implant. In soft tissues a fibrous capsule is formed around the implant (phenomenon of walling off the material from the biological environment) (Thomsen and Ericson, 1991). In bone,
20 encapsulation of the implant by fibrous tissue may occur but is not obligatory and instead mineralized bone can establish direct contact with the implant, a process called osseointegration (Brånemark et al., 1969). Although the work on cell-material interactions has been intensified
25 during recent years, the mechanisms by which material properties influence biological reactions are still not clear. Studies in vitro.

The attachment of tissues to implants *in vivo* is a complex matter because in most cases there are different types of
30 tissues involved which may behave differently at different surfaces. The response of cells to variations in culture substrate topography varies for different cell types like macrophages (Rich and Harris, 1981; Salthouse, 1984), fibroblasts (van der Valk et al., 1983), periodontal cells

(Cochran et al., 1994), epithelial cells (Chehroudi et al., 1989; Chehroudi et al., 1990), osteoblasts (Bowers et al., 1992; Martin et al., 1995) and chondrocytes (Schwartz et al., 1996).

5 Rich and Harris (1981) showed that macrophages accumulated preferentially on less hydrophilic as well as on roughened substrata. Murray et al (1989) showed that when macrophages adhered to hydrophilic surfaces PGE₂ release and bone
10 resorption was stimulated compared with hydrophobic surfaces. In addition, the rough surfaces was found to stimulate bone resorption to a greater extent than smooth surfaces. Although the roughness and the surface energy of the different surfaces were not quantitated this indicates that the interactions between macrophages and implant
15 surfaces cause a release of factors which is higher than if cells are in suspension. Studies on human monocyte interactions with titanium surfaces have shown that the interleukin-1 release by the cells is modulated by protein adsorption and the presence of material particles (Gretzer
20 et al., 1996).

Interestingly, different results have been obtained with fibroblasts. Human fibroblasts attached better to smooth than to rough titanium surfaces, (polished with 1 µm diamond paste versus the rougher; prepared with 240 or 600
25 grit silicon carbide metallographic papers) (Keller et al., 1989). Spreading of fibroblasts was found to depend on the polar surface free energy (van der Valk et al., 1983) since at least on various polymer surfaces, low cell spreading was found on low polar parts. Sukenik et al (1990) modified
30 titanium surfaces with different covalently attached self-assembled monolayers (four different chemical endgroups; CH₃; C=C; Br; Diol). The neuroblastoma cell attachment to the different surfaces was comparable but cell spreading was least pronounced on the most hydrophobic surface (CH₃

and C=C).

Osteoblasts are sensitive to subtle differences in surface roughness and surface chemistry and respond to altered surface chemistry by altering proliferation, extracellular matrix synthesis, and differentiation (Boyan et al., 1995). Osteoblasts exhibited different phenotypes when cultured on rutile or amorphous TiO₂ surfaces, but with the same oxide thickness and degree of roughness. Differences were therefore suggested to be attributed to crystallinity alone (Boyan et al., 1995).

Osteoblasts have an initial greater attachment to rough, sandblasted titanium surfaces with irregular morphology but average roughness (R_a) parameters did not predict cell attachment and spreading *in vitro* (Bowers et al., 1992).

Proliferation and differentiation parameters in osteoblast-like cells were modified by growing cells on titanium discs with an increased roughness (15-18 μm) (Martin et al., 1995). Interestingly, cells at different stages of differentiation responded differently to the same surface (Boyan et al., 1995; Schwartz et al., 1996).

A basis for most studies *in vitro* on the role of surface properties for cell function is the adhesion of cells to the surface of the culture dish. The resulting interactions between the cell and the surface, with or without adsorbed molecules, is therefore a fundamental and obvious part of the experimental set-up. In this context it may also be argued that the properties of the material surface as stimulating or inhibiting factors on cells could be over-emphasized in relation to other potential and maybe equally important modulating factors present in the vicinity of cells and surfaces in the complex biological situation *in vivo*.

Studies on titanium implants in bone (Sennerby et al.,

1993a; Sennerby et al., 1993b), indicated that osteoblasts did not adhere to the implant surface and that formation of bone was not initiated at the surface. This observation suggests that the studies on the interaction between
5 osteoblasts and titanium surfaces *in vitro* is of minor relevance. Nevertheless, studies *in vitro*, where various aspects of the complex *in vivo* situation can be studied in detail may be of great value but this requires that the conditions *in vivo* are considered when the *in vitro* system
10 is designed.

On the basis of the published *in vitro* studies it may be concluded that the surface roughness appears to influence the cell proliferation albeit differently depending on the degree of cell maturation. Differences in surface
15 properties may influence the cell attachment and proliferation although the mechanism is not clear. It is also evident that different cell types are differently influenced by the surface properties. However, so far there are few studies on the effect of modified titanium surfaces
20 on cellular behaviour. A review of the literature on the *in vivo* response to titanium implants is therefore appropriate.

In general, histology, histochemistry and immunohistochemical techniques have been used for the
25 evaluation of soft tissue reactions. Due to technical difficulties to obtain thin sections of an intact metal-tissue interface the ultrastructure of the interface tissue has been difficult to study (Ericson and Thomsen, 1995). However, for metals in soft tissues, an electropolishing
30 method by which the bulk metal, but not the thin surface oxide layer, is removed (Bjurstén, 1990) have made such studies possible.

The macrophage plays a pivotal role during healing of soft tissue around implants. The soft tissue response to

titanium implants in rats is described by Thomsen and Ericson in (Brånemark et al., 1995). A fluid space, containing cells and proteins was present during the early phase (1-2 weeks) after introduction of a titanium implant
5 in soft tissues (Johansson et al., 1992; Röstlund et al., 1990). The concentration of leukocytes and the proportion of PMN in the fluid space decreased between 1 and 7 d (Eriksson et al., 1994). After one week the majority of inflammatory cells in the fluid space, predominantly
10 monocytes and macrophages, were attached to the fibrin matrix at the border between the fluid space and the reorganized tissue rather than to the implant surface. After six weeks the fluid space was largely absent and the macrophages had established contact with the implant
15 surface (Johansson et al., 1992; Röstlund et al., 1990). Macrophages constituted the most common cell type at the titanium surface, and exhibited different phenotypes, as judged by their ultrastructure (Johansson et al., 1992). Immunohistochemical observations (Rosengren et al., 1993)
20 show that the fluid space around a titanium implant one week after implantation contained albumin, complement factor C3c, immunoglobulins, fibrinogen and fibronectin. Albumin and C3c were distributed in the fluid space and throughout the tissue interstitium during the first week.
25 Fibrinogen and fibronectin co-localized preferentially at the border between the fluid space and the tissue, thus forming a provisional matrix to which macrophages and fibroblasts adhered.

After 6 and 12 weeks, fibrinogen was not detected in the
30 surrounding tissue whereas strands of fibronectin was found in the surrounding capsule (Rosengren et al., 1996). Collagen type I immunoreactivity, coinciding with the collagen bundles in the surrounding tissue, had a distribution similar to that of fibronectin, reaching close

to the titanium surface, but always separated from it by one to several layers of macrophages after 12 weeks.

The general sequence of cellular migration and accumulation as well as the leakage of plasma into the tissue in the immediate vicinity of the implant surface has been observed after implantation of several different materials, including metals, in soft tissues (Thomsen and Ericson, 1991). The tissue response around nitrogen-ion implanted titanium discs inserted in the rat abdominal wall of rats was not significantly different from that observed around pure titanium implants. However, after 6 weeks a predominance of macrophages and multinuclear giant cells was found around the nitrogen-ion implanted discs (Röstlund, et al., 1990). A comparison of titanium and Ti6Al4V after 1, 6 and 12 weeks in the same rat abdominal wall model did not reveal any differences with regard to cell types and numbers in the interface (Johansson et al., 1992). Further, the authors did not find any difference in fibrous capsule width. Therin et al. (1991) showed similar results when comparing the capsule thickness for titanium, TiO₂-coated titanium, Ti6Al4V, TiO₂-coated Ti6Al4V, TiN-coated Ti6Al4V, Ti5Al2.5Fe and stainless steel (316 L).

In contrast to polymers (Chehroudi et al., 1989; Chehroudi et al., 1990) studies in soft tissues which have been focused on the biological effects of altered surface topography and roughness of metal implants are relatively few.

However, in an extensive light microscopical study on the effects of surface roughness variations of titanium and stainless steel, (Ungersböck et al., 1994) it was shown that smooth implants induced a thicker soft tissue capsule with an intervening fluid space. In contrast, blasted and anodized titanium plates with relatively high values of roughness parameters (Ra 0.75) were surrounded by a

significantly thinner soft tissue layer without a continuous liquid space. On the basis of these results it is difficult to conclude that there exists a simple relationship between increased surface roughness and capsule thickness. For instance, Al_2O_3 -blasted titanium plates with an even greater surface roughness (R_a 1.5) had a capsule thickness which was similar to that around blasted, anodized titanium samples. Further, tumbled titanium plates (R_a 0.15) had a capsule thickness which was similar to tumbled and anodized smooth titanium (R_a 0.33). The roughness was measured with a profilometer and the elemental composition of implant surfaces was not reported. It is therefore possible that the surface chemical composition and/or roughness on the submicrometer level, differed between the samples. Studies on the effects of various surface topographies (smooth vs. various microtextures between 1 and 10 μm) of titanium discs implanted in soft tissues of rabbits showed that collagen type III immunoreactivity was detected in the fibrous capsule around several materials, but that collagen type I was positively stained only in capsules around titanium (von Recum et al., 1993).

In general, the experimental studies in soft tissues indicate that metals become surrounded by a fibrous capsule with macrophages located closest to the surface, thus separating fibroblasts from the surface. So far there are few available morphological data on the interface structure around titanium surface modifications. It is still an open question how the material surface properties influence protein adsorption during *in vivo* conditions and how the surface properties influence the cells close to the surface. Moreover, it is not understood how the composition and structure of the surrounding fibrous capsule is influenced by the material surface-macrophage interactions.

It is likely that several additional factors must be considered, including leaching of metal ions, loading conditions and micromovements between the implant surface and tissue.

5 The response of bone to injury is regeneration followed by remodelling of the newly formed bone in the direction of stresses. Analogously, when an implant is inserted in bone, a similar cascade of events is expected to occur including the recruitment of mesenchymal cells to the wound
10 site, their differentiation into osteoblasts, synthesis of osteoid, and calcification of the extracellular matrix. The mesenchymal progenitor cells are pluripotent and able to differentiate into osteoblasts, chondrocytes, muscle cells and fat cells (Caplan and Boyan, 1994). The pathway of
15 differentiation of the mesenchymal cells as well as regeneration of bone around an implant is most likely dependent on a combination of factors including the degree of trauma, local and systemic factors as well as implant properties and stability.

20 In the following a short summary of previous work on the interaction between metal implants and bone will be given. The performance of non-metal implants is reviewed elsewhere (de Groot et al., 1994).

Studies comparing the performance of, different implants of
25 metals including Vitallium®, niobium, titanium, titanium alloy, stainless steel (Johansson et al., 1991), and zirconium (Albrektsson et al., 1985; Johansson et al., 1994) in bone, did not reveal any major qualitative differences. The threaded titanium implants were in general
30 found to be in contact with more mineralized bone than the other types of metal. The mechanisms for this is not clear nor is it understood why the properties of titanium are advantageous for biological applications compared with other metals, including those nearby in the periodic

system. The good biological performance of titanium has been attributed to the titanium oxide layer covering the surface, but no compelling evidence for this view has been presented.

5 Several studies have indicated that an increased roughness of implant surfaces (within a certain range) enhance the biomechanical performance of implants. However, the bone response seldom show differences although some studies indicate an increased bone-implant contact with increased
10 surface roughness (Buser et al., 1991; Goldberg et al., 1995; Gotfredsen et al., 1995). Most studies did not reveal such a correlation (Carlsson et al., 1988; Gotfredsen et al., 1992; Thomas and Cook, 1985; Thomas et al., 1985; Thomas et al., 1987; Wennerberg 1996; Wilke et al., 1990; Wong et al., 1995). Brånemark (1996) made a correlation
15 between morphological parameters of osseointegration of threaded titanium implants and different biomechanical tests and found that pull-out tests mainly reflects the mechanics of the surrounding bone while removal torque
20 tests reflects the shearing forces leading to plastic deformation of the bone-implant interface. Possibly biomechanical tests performed on implants with a rough surface (micrometer level), inserted in bone mainly reflect the bone-material mechanical interaction (interlocking)
25 although it cannot be excluded that differences in the structure of the interface not resolved by light microscopy are of importance.

Using an animal model similar to that used in the present study Sennerby et al (1993b), studied the bone response 3-
30 180 days after insertion of screw-shaped titanium implants. At 3 days mesenchymal cells were migrating into the injury area around the implants. The implant surface was temporarily covered by multinuclear giant cells which disappeared with time and when bone-titanium contact

increased. Newly formed bone extended from the endosteal surface towards the implant and was also formed as islands within the implant threads.

With time the two types of newly formed bone fused. The
5 threads originally protruding into the marrow cavity were gradually filled with bone which matured by remodelling. Formation of new bone directly at the titanium surface was not observed at any time interval.

Only a limited number of studies of the ultrastructure of
10 the bone-metal interface tissue are available. This may reflect the fact that the preparation of the interface tissue for analysis by transmission electron microscopy TEM is technically demanding, especially when the decalcification step is omitted.

15 Albrektsson et al (1982) introduced polycarbonate plugs coated with a thin layer of evaporated metal as a model for metal implants. The plugs were implanted in the rabbit tibia. TEM on partially decalcified specimens showed the presence (after 3 months) of collagen bundles close to
20 titanium implant but the last 100-500 nm closest to the implant consisted of randomly arranged filaments. A 20-40 nm thick layer of partially calcified amorphous substance, suggested to consist of proteoglycans was found in contact with the implant surface. A gradient of decreasing
25 mineralization towards the implant surface was also described. In contrast, a larger number of macrophages and osteocytes were found at gold-coated plugs. In more recent studies based on the plastic plug technique, other metal coatings including zirconium has been compared with
30 titanium (Albrektsson and Hansson 1986; Albrektsson et al., 1985).

Linder et al (1989), studied the interface morphology of plugs of titanium. Ultrastructural observations in rabbit

cortical bone (11 months observation period) adjacent to titanium, Tivanium®, Vitallium®, and stainless steel revealed an unpredictable variation in interface ultrastructure within 500-1000 nm of all metal surfaces.

5 Three main types of interface structure were found; a) More or less regularly arranged fibrils of collagen, with the longitudinal cross-banding of 68 nm typical of type-I collagen, approaching the metal surface to within 50 nm; b) Type-I collagen fibrils separated from the implant by a
10 zone of indistinct structures, but with some filamentous material, most often about 500 nm in thickness, but sometimes up to 1000 nm; c) Type-I collagen fibrils separated from the implant by a 500-600 nm zone of thin filamentous structures, clearly more dense than in b. There
15 was no structural feature that was specific for a particular material (Linder et al., 1989).

Sennerby et al (1992) examined the interface morphology of titanium implants inserted into the rabbit tibia for 12 months and found mineralized bone to be present very close
20 to the implant surface without any apparent decreasing gradient of the concentration of bone mineral towards the implant surface. A thin layer of amorphous non-mineralized material (100-200 nm wide) was present peripheral to the mineralized bone. In addition, visible when mineralization
25 was low, an about 100 nm wide electron dense lamina limitans was found to form the border between mineralized bone and the amorphous layer. This lamina limitans were often seen in direct continuity with lamina limitans bordering osteocyte canaliculi or separating bone of
30 different mineralization grades.

Steflik studied the interface morphology at various types of implants in the dog mandible using TEM and high voltage TEM and found an about 50 nm wide electron dense deposit at the implant surface (Steflik et al., 1992a; Steflik et al.,

1992b). No difference was seen between loaded and unloaded implants (Steflik et al., 1993). Nanci et al (1994) studied the tissue response to titanium implants inserted for 1 day to 5 months in tibia and femur of rats. The morphology of the interface tissue varied. Most often the interface between bone and the titanium implant consisted of a thin, electron-dense layer. This interfacial layer was found both adjacent to mineralized bone and unmineralized collagen. With immunocytochemical techniques, the electron-dense layer described as lamina limitans was shown to be immunoreactive for osteopontin. The cement lines in the surrounding bone often in continuity with the lamina limitans at the implant surface, showed a similar immunoreactivity for osteopontin. Osteocalcin, fibronectin, and albumin showed no preferential accumulation at the interface. In a recent study McKee and Nanci, (1996) are suggesting that osteopontin functions as a mediator of cell-matrix and matrix-matrix/mineral adhesion during the formation, turnover and repair of mineralized tissue. A review of the literature on the soft tissue response to titanium implants is important since a penetration through skin and mucous membranes is necessary to allow the attachment of external prosthetic appliances (e.g. teeth and epistheses). Interest has been focused on the prerequisites for an adequate adaptation of the soft tissue to the penetrating element. Empirically it has been found that a careful surgical technique with minimal motion at the interface by a tight adherence of the soft tissues to the underlying bone may provide adequate conditions for clinical percutaneous and permucosal implants/anchorage units.

In studies on the relationship between the titanium surface and epithelium and connective tissues the majority of observations in humans have been made in specimens from the

oral cavity (Sanz et al., 1991; Seymour et al., 1989; Tonetti et al., 1993) and from the craniofacial region (bone conductive hearing aids) reviewed in (Holgers 1994). In a light microscopic and ultrastructural study of oral
5 implants (Sanz et al., 1991) the inflammatory infiltrates were scarce in the non-infected peri-implant tissue. However, when gingivitis was observed, the inflammatory infiltrates were larger, dominated by mononuclear cells and plasma cells. (Seymour et al., 1989) characterized the
10 mucosa around Brånemark osseointegrated titanium implants. The samples were obtained from healthy mucosa or with clinical signs of inflammation (gingivitis). The authors reported the presence of inflammation in both situations (healthy gingiva or gingivitis) but found larger
15 inflammatory infiltrates and higher cell numbers when clinical signs of gingivitis were present. The authors concluded that the mucosal reaction was a stable and well controlled response. Similar findings were reported around clinically functioning bone-anchored percutaneous implants
20 (Holgers, 1994), suggesting that an immunological compensation for the loss of barrier function is present at implants with clinically irritated skin. The relationship between epithelial cells and the surface of implants as well as the common observations of epithelial downgrowth
25 have been suggested to play an important role for the function of implants, both in oral and percutaneous applications. In contrast to observations for dental implants (Listgarten and Lai, 1975; Schroeder et al., 1981), no close contact between the epithelium/collagenous
30 tissue and the surface of percutaneous titanium implants were seen (Holgers et al., 1995).

In conclusion, these observations indicate that machined titanium implants in soft tissues of humans are surrounded by inflammatory cells which appear to provide a protective

barrier which may compensate for a non-optimal epithelial barrier.

Analysis of a retrieved osseointegrated clinical titanium implant (3 months) (Lausmaa J. 1988) revealed an increased
5 oxide thickness (by factor 2-3) compared with an unimplanted sample. Similar in vivo oxide growth have been reported earlier. By the use of Auger electron spectroscopy, McQueen et al. (1982) observed that after 6 years in human jaw bone, the original 50 Å thick oxide
10 layer on titanium implant surfaces had increased to a 2000 Å thick oxide layer.

Sundgren et al (1986) investigated the interface of bone-titanium and bone-stainless steel in humans and found that both the thickness and the nature of the oxide layers on
15 the implant had changed during the time of implantation. Depending on the location, the thickness remained unaffected (cortical bone) or increased with 3-4 times (bone marrow). In both cases, Ca and P were incorporated in the oxides. For titanium implants the oxidation process
20 occurred over a longer time period (several years).

In a light microscopical study by Sennerby et al. (1991), seven clinically stable (1-16 years) osseointegrated dental implants, were analyzed morphometrically. The major part of the implants were in contact with mineralized bone (56-
25 85%), irrespective of observation period. Carlsson et al (1994) evaluated the tissue around implants with different roughness inserted experimentally in arthritic knees. Blasted titanium and hydroxyapatite-coated implants were in contact with bone whereas smooth titanium implants often
30 were surrounded by fibrous tissue .

Sennerby et al (1991), examined the structure of the interface around seven clinically stable dental implants (1-16 years) by morphometry. In areas with mineralized bone

close to the titanium surface, a non-mineralized amorphous layer was observed. An electron dense lamina limitans-like line was observed between the mineralized bone and the 100-400 nm wide amorphous zone.

5 Ultrastructural observations were made on the metal-bone of interface of implants inserted in the tibia of patients with arthrosis and rheumatoid arthritis (7-20 months) (Serre et al., 1994) The implants were all screw-shaped pure titanium implants and they were all
10 ``osseointegrated''. No difference between the ultrastructure of the interface between normal bone and implants compared with the interface of arthrotic and arthritic bone was observed. The heterogeneity of the interface was also confirmed in this study although the
15 100-400 nm wide amorphous zone reported by Sennerby et al (1991), was not found.

In an ultrastructural study of the interface of a plasma-sprayed titanium dental implant inserted in man (ITI), (Hemmerlé and Voegel, 1996), two different interfacial
20 structures were noticed. Both bone crystals directly apposed on the implant surface and a granular electron-dense substance interposed between the plasma-sprayed coating and the bone were observed. Rohrer et al (1995) examined non-decalcified histologic sections from 12
25 osseointegrated titanium plasma spray-coated (TPS) and TPS-treated with hydroxyapatite implants (IMTEC) from one patient. All implants were successful and stable after 1 year when the samples were retrieved. Both implant types were used with the same success and no morphological
30 differences were observed between the two implant types.

The following invention is based on a comprehensive experimental study using differently modified titanium surfaces. In the following the experimental procedures are summarized. Details may be found in a thesis, (C. Larsson:

The Interface between bone and metals with different surface properties) including the following papers;

- I. C. Larsson, P. Thomsen, J. Lausmaa, M. Rodahl, B. Kasemo and L. E. Ericson. Bone response to surface modified titanium implants. Studies on electropolished implants with different oxide thicknesses and morphology. Biomaterials 1994 (15) 13, 1062-1074
- II. C. Larsson, P. Thomsen, B-O Aronsson, M. Rodahl, J. Lausmaa, B. Kasemo and L. E. Ericson. Bone response to surface modified titanium implants. Studies on the early tissue response to machined and electropolished implants with different oxide thicknesses. Biomaterials 1996 (17) 6, 605-616
- III. C. Larsson, P. Thomsen and L. E. Ericson. The ultrastructure of the interface zone between bone and surface modified titanium. (In manuscript)
- IV. C. Larsson, P. Thomsen, B-O Aronsson, M. Rodahl, J. Lausmaa, B. Kasemo and L. E. Ericson. Bone response to surface modified titanium implants. Studies on the tissue response after one year to machined and electropolished implants with different oxide thicknesses. Journal of Materials Science: Materials in Medicine, submitted
- V. C. Larsson, P. Thomsen, J. Lausmaa, P. Tengvall, B. Wälivaara, M. Rodahl, B. Kasemo and L. E. Ericson. Bone response to surface modified titanium implants. Studies on the early tissue response to different surface characteristics. (In manuscript)

Threaded screw-shaped implants were manufactured by machining of: pure titanium (grade I, 99.7%) (Permascand, Ljungaverk, Sweden)

The implant surfaces were modified with different

preparation techniques (summarized in table I). Details of the different surface modifications are found in the separate papers (I-V). All implants had a length of 4 mm and a diameter of 3.75 mm.

- 5 Circular, disc-shaped implants (\varnothing 10 mm, thickness 1.8 mm), were manufactured by machining of a titanium rod (99.7%) (Permascand, Ljungaverk, Sweden). These implants were used for studies on protein adsorption *in vitro* and inflammation in soft tissues.
- 10 The techniques for preparation and surface modification of the three types of implants (machined, electropolished, and electropolished plus anodized) used in the additional experiments a) and b), are described in detail in paper I and II.
- 15 During the electropolishing technique the sample is used as an anode in an electrochemical cell. By varying the electrolyte composition and process parameters (temperature, voltage and current) in the cell, various surface treatments can be carried out, including
- 20 electrochemical polishing (electropolishing) or anodic oxidation (anodization).

The electropolishing technique which acts as a controlled electrochemical dissolution of the surface (Landolt, 1987), was carried out at 22.5 V in an electrolyte consisting of a

25 mixture of 540-600 ml methanol, 350 ml butanol and 60 ml perchloric acid held at -30°C . Each sample was polished for 5 min. which is estimated to remove less than 100 μm of material from surface. The electropolishing procedure was carried out in order to produce a smooth, mirror-like

30 surface finish. It also has the effect of removing the plastically deformed amorphous surface layer which results from machining of the material. After electropolishing, the samples were carefully rinsed in methanol in order to

remove electrolyte residues.

Anodic oxidation (anodization) (Ross, 1975) was carried out at 80 V in a M acetic acid electrolyte at room temperature. This procedure produced a vivid, greyish-purple colouration of the surface, due to light interference in the thick oxide that was formed. It is well established that the oxide thickness is linearly dependent on the applied voltage, with a growth constant. $\alpha \approx 2-3 \text{ nm/V}$ for titanium, depending on experimental conditions. The anodized samples were carefully rinsed in deionized water followed by a rinse in ethanol.

Scanning Auger electron spectroscopy (AES; Perkin-Elmer PHI 660, Eden Prairie, USA) was used to analyze the surface elemental composition. Oxide thickness was estimated from AES depth profile analysis. At least 2 different spots ($\varnothing 100 \mu\text{m}$), located at the threaded part of the sample were analyzed. Depth profiles were obtained at 2 points ($\varnothing 10 \mu\text{m}$).

AES survey spectra were acquired from two areas of $\varnothing 200 \mu\text{m}$ on one sample of disc-shaped machined, electropolished and electropolished plus anodized titanium implants.

Scanning electron microscopy (SEM; JEOL JSM-T-300, and Zeiss DSM 982 Gemini) was used to obtain an overall picture of the surface topography. Atomic force microscopy (AFM; Nanoscope III, Digital Instruments, USA) was used for a more detailed characterization of the surface topography and roughness. The surface roughness (R_{rms}) and surface area enlargement (A_{diff}) were calculated using the computer software of the AFM instrument.

Contact angles were measured using a Ramé-Hart goniometer, model 100. Advancing and receding contact angles were determined for titanium (control), electropolished and electropolished plus anodized samples, both with Millipore

filtered water and with methylene iodide. One drop (5 μ l) of the liquid, was placed on three different spots on each sample. Both right and left angles of the drop were estimated and the mean values calculated. The samples were
5 cleaned (in addition to the conventional cleaning steps with trichlorethylene, acetone, and ethanol) with 95% ethanol and air-dried within 30 min prior to analysis. Surface energy was calculated and preferred values of surface tension for the liquids in room temperature (Wu,
10 1982) were used for water and methylene iodide.

The implants were ultrasonically cleaned in trichlorethylene; acetone; methanol. After surface modification (electropolishing and/or anodic oxidation), all implants received a final ultrasonic cleaning step in
15 ethanol (70%). Finally, implants were either autoclaved in 120 °C for 15 min. or γ -irradiated at 28.9 kGy for 25 h at 30° C. The hydrogen peroxide treated implants were treated with 10 mM H₂O₂ for 40 h at 8° C after the ultrasonically cleaning procedure. No additional sterilization was
20 performed.

The disc-shaped implants were ultrasonically cleaned in trichlorethylene; acetone; ethanol. After surface modification (electropolishing and/or anodic oxidation), all implants received a final ultrasonic cleaning step in
25 ethanol.

Rat plasma was obtained from two rats and used in protein adsorption experiments.

Fifteen Sprague-Dawley rats, weighing about 250 g, were used for studies on cell recruitment and adhesion to
30 titanium surfaces in soft tissues.

The surgery was performed according to procedures described earlier, (paper I-V) and implantation was made bilaterally in the proximal tibial bones. After incision through the

skin and periosteum, a flap was raised to expose the bone area. Thus, each animal received one implant of each type, respectively.

After the animals were killed, the implants and surrounding
5 tissue were removed en bloc, further immersed in glutaraldehyde over night and then postfixed in 1% osmium tetroxide, for two hours. After dehydration the undecalcified specimens were embedded in LR White[®] (The London Resin Co Ltd, Hampshire, England).

10 In studies on protein adsorption in vitro surface adsorbed proteins were collected, separated (SDS-PAGE) and visualized (Western blot). In brief, discs were kept in 99.5 % ethanol, ultrasonicated in 99.5 % ethanol, washed three times and kept in 99.5 % ethanol until use. Before
15 incubation with proteins, the samples were placed in sterile-filtered HBSS with calcium. Rat plasma was incubated on three surfaces of each kind (machined, electropolished and electropolished plus anodically oxidized titanium) during 1 min. at 37° C. Thereafter
20 loosely attached proteins were rinsed off and the surface adsorbed proteins removed by the detergent SDS (2%) together with enzyme inhibitory agents. The total amount of collected proteins was analyzed with BCA Protein Assay Reagent (Pierce, USA) using spectrophotometry (562 nm) and
25 with rat albumin as standard. Gel electrophoresis with precasted Tris-glycine (4-15 %) gradient acryl amide gels (BioRad, Miniprotean II) was performed to separate the proteins. After separation the proteins were transferred to nitrocellulose membranes (70 V, 3 h, Tris-glycine-SDS
30 buffer) followed by blocking of unspecific antibody binding by incubation in 3 % gelatin in Tris-NaCl buffer, pH 7.5. To detect specific proteins on the membrane 3 incubation steps were performed (60 min., room temp.) in Tris-NaCl-Tween buffer.

The primary step included rabbit anti-rat fibronectin (FN); goat anti-rat fibrinogen (fraction1) (FBN); sheep-anti-rat albumin (Alb); sheep anti-rat immunoglobulin G (IgG). The secondary step included biotinylated donkey anti-sheep IgG; 5 biotinylated goat anti-rabbit IgG and the tertiary step included streptavidin conjugated to alkaline phosphatase in Tris-NaCl-Tween (TTBS) buffer. Visualization of the labelled proteins (samples and standard) was made by incubation in BCIP/NBT.

10 The implantation of implants in soft tissues was performed according to previously described procedures (Lindblad M. et al., 1997). In brief, 15 Sprague-Dawley rats, weighing about 250 g, were anesthetized with an i.p injection (0.1 ml/100 g b.wt.) of a 1:1:2 solution of sodium pentobarbital 15 (Apoteksbolaget, Sweden; 60 mg/ml), 0.9 % saline and diazepam (Apozepam®, Apothekarnes Laboratorium AS, Norway; 5 mg/ml). The rats were shaved on the dorsum and cleaned with 2 % Jodopax® in ethanol. Incisions, about 15 mm long and 10 mm apart were made in the dorsal skin along the 20 midline. Subcutaneous pockets were created by blunt dissection and implant discs were placed in the pockets using a pair of titanium tweezers. In six rats three incisions were made along each side of the midline. These rats received two of each type of implant: one of these two 25 implants was rinsed in sterile HBSS buffer (Hanks balanced salt solution with CaCl₂ 2.9 g/l, pH 7.4) whereas the other implant was rinsed in sterile saline. The other nine each received three implants, one of each type, which were rinsed in saline prior to insertion. The skin was closed 30 with non-resorbable sutures. After 1 (n=6), 3 (n=6) and 7 (n=3) days the dorsal skin of anaesthetized rats was cleaned and the rats killed by an i.p. overdose of pentobarbital. The sutures were taken away and the wound surfaces were gently drawn apart with tweezers. The

implants were removed and placed in a sterile polystyrene tissue culture dishes, containing 500 μ l sterile HBSS (with calcium) and kept on ice. The remaining content (exudate) of the cavity was collected by rinsing, using repeated
5 aspirations (5 times) of 500 μ l (total volume) sterile HBSS (with calcium).

Each retrieved exudate was kept on ice until the determination of cell count and cell types. The exudates were stained with Türk solution and the proportion of
10 different cell types was determined. The total mean of the number of cells found in the exudate was calculated from six (1 and 3 d) and three (7 d) rats per time period and the percentage mean values of different cell types were calculated in the same way.

15 The determination of the amount of DNA associated with the implant surfaces was performed with a fluorescence assay (Labarca C. and Paigen K. 1980). In brief, after the retrieval procedure each implant was put in 500 μ l 5×10^{-2} M sodium phosphate buffer with 2×10^{-3} M EDTA and 2 M
20 NaCl. Thereafter, the implants were frozen at -20° C. After thawing and ultrasonication of the cells on the implants (about 15 s at each side of the implant), 200 μ l of the solution was added to 5×10^{-2} M sodium phosphate buffer with 2 M NaCl, supplemented with 1 μ g ml $^{-1}$ of the
25 fluorescence marker Hoechst 33258 (Sigma, USA) at room temperature (15-30 min.). The samples were measured in a luminescence spectrometer with excitation and emission wavelengths of 360 and 450 nm, respectively. The total amount of DNA was determined from standard curves (0.025-
30 2.5 μ g DNA per ml). The total mean of the DNA amount associated with the implant surfaces was calculated from six (1 and 3 d) and three (7 d) rats per time period.

Ground sections of 10-15 μ m thickness were prepared from implant/bone specimens (Donath and Breuner, 1982), and

examined, using a Leitz Microvid equipment connected to a personal computer. Measurements were performed directly in the microscope. The contact ratio between the implant surface and bone tissue was calculated. Similarly, the proportion of bone tissue within the threads along the implant was calculated. The data are given as percentage bone in direct contact with the implant (referred to as bone contact) and percentage of the total area within the threads occupied by mineralized bone (referred to as bone area). All five consecutive threads (with number 1 and 2 located in the cortex) were evaluated. In the one-year study, the values for the 3 best consecutive threads were also presented. The mean value for each implant type at each time period was calculated and compared. After polymerization embedded implants were divided longitudinally by sawing. One half was used to prepare ground sections (Donath and Breuner, 1982) which were used for morphometric analysis (papers I-II, IV-V) as described above. The other half was used for the preparation of sections for light and electron microscopy (papers I, IV). The implant was carefully separated from the plastic embedded tissue (Sennerby et al., 1992; Thomsen and Ericson, 1985). The cavity formed after implant removal was filled with plastic resin and polymerized before sections for LM (approximately 1 μ m thick) were cut with glass knives. In these sections appropriate areas were selected for ultramicrotomy. Ultrathin sections, contrasted with uranyl acetate and lead citrate were examined in Philips EM 400 or Zeiss CEM 902 electron microscopes.

30 RESULTS

A summary of the results from surface characterization of the different samples (papers I-V) is presented in Table I. Machined (control), electropolished, electropolished plus anodized (21 nm thick oxide) and electropolished plus

anodized (180 nm thick oxide) were used in paper I and III. The machined titanium implants (control) had typical machining grooves in the width of 1-10 μm . The electropolished implants had a very smooth, mirror-like surface with no apparent surface features at low or high magnification. The anodized (21 nm) samples also appeared smooth whereas the anodized (180 nm) had porous regions irregularly distributed over the smooth surface which made the implant surface roughness heterogeneous (1 μm scale). R_{rms} values obtained by AFM are presented in Table I.

Machined (control), machined plus anodized (180 nm thick oxide) electropolished, and electropolished plus anodized (180 nm thick oxide) were used in paper I and III.

The machined (control) and machined plus anodized surfaces had a similar surface appearance with typical machining grooves in the width of 1-10 μm . The machined plus anodized surface also showed an additional, irregular surface roughness on the submicron level. The electropolished surface appeared very smooth whereas the electropolished plus anodized surface presented a heterogeneous surface with irregularly distributed smooth and rough (10-100 μm large) areas. No machining grooves were visible on the surfaces of the two groups of implants that had been electropolished. R_{rms} values obtained by AFM are presented in Table I. Scanning electron micrographs are shown in Fig. 1 (electropolished + anodized implant, a-c; machined + anodized implant, d). AFM images are shown in Fig. 2 (electropolished + anodized implant a = rough part, b = smooth part; machined + anodized implant, c).

30 Paper V:

In this paper machined, glow discharge cleaned and thermally oxidized, glow discharge cleaned and nitrided and hydrogen peroxide treated implants were used.

The machined (control) surface had the characteristic grooves, 1-10 μm in width as described above. The two groups which were plasma cleaned and subsequently oxidized and nitrided, respectively, had similar surface topography.

5 The underlying grain structure could be seen although grooves from the machining procedure were clearly visible. The hydrogen peroxide treated implants showed clear traces from the machining procedure and had a woolly surface which reflects the etching action of the treatment.

10 Surface composition and thickness of surface layers

The results of the AES analyses are summarized in Table I.

Papers I, III

All samples had a relatively consistent surface composition independent of preparation. All spectra were dominated by
15 strong Ti, O and C signals and trace amounts of Ca, S, Si, P, Cl and Na were detected. Ca and S appeared more frequently on the control samples than on the electrochemically prepared ones. Lower levels of C and other contaminants were found on the anodized (80V)
20 samples. The depth profile analysis resulted in oxide thicknesses of 4, 4-5, 21, and 180 nm for the control, electropolished, electropolished/anodized (10V) and electropolished/anodized (80V) implants, respectively.

Papers II, IV

25 Irrespective of surface preparation all samples had a relatively similar surface composition with strong Ti, O and C signals in the spectra. The carbon contamination varied between the different samples from $\dot{\text{A}}$ 34 at% for the machined and machined-anodized samples to $\dot{\text{A}}$ 25 at% for the
30 two electropolished samples. Trace amounts Ca, S, P, Si were detected (few percent).

Paper V

On all samples Ti, O or N/O and C were the dominant elements. All samples showed relatively low levels (10-15 at%) of carbon contamination on the surfaces compared to
5 other studies (typically 30 at% or more) (Lausmaa J. 1996). The oxides on the control, glow-discharge oxide and H₂O₂ treated samples respectively, were nearly stoichiometric titanium dioxide and of similar thickness (4-7 nm).

In additional experiments:

10 The disc-shaped implants used for studies on protein adsorption and inflammation in soft tissues consisted of a TiO₂ surface oxide covered by varying amounts of hydrocarbons and other trace impurities. For the machined control sample, carbon levels around 50%, and around 4% Ca
15 and minor traces of S and P were detected. For the electropolished sample around 30% C was detected, and traces of Ca, S, and Cl. The electropolished plus anodized sample had carbon levels around 20%, and around 6% Ca and traces of S, Cl, Si and Fe. Except for the variations in
20 carbon levels, the disc-shaped samples had a similar surface composition as the corresponding surfaces of threaded implants used in the previous studies (paper I-V).

Contact angles and surface energy

The contact angles were measured on the circular disc-
25 shaped implants since it is not possible to measure the contact angle on a screw-shaped implant (Table II and III). The contact angle (H₂O advancing) was lower for the electropolished plus anodized implant than for the machined and electropolished samples. Due to porosities of the
30 electropolished plus anodized surface, capillary forces may spread the water, thus giving a lower water contact angle (Andrade, 1985). The electropolished plus anodized surface had the greatest hysteresis (difference between the

advancing and receding angle) when measured with methylene iodide. Increased surface roughness and differences in topography may lead to increased hysteresis. Since all surfaces have a similar chemical composition, all surfaces will have the same ``real'' contact angle although the surface topography will influence the measured value.

The tissue response

Protein adsorption in vitro

Our observations show that there are only small differences in the protein adsorption pattern between the machined, electropolished and electropolished plus anodized titanium surfaces. The total amount of adsorbed plasma proteins was similar on the three surfaces. The protein concentrations obtained were for machined titanium 1.15 mg/ml, electropolished titanium 1.05 mg/ml and electropolished plus anodized discs 1.25 mg/ml, respectively. Further, the content of selected plasma proteins, albumin, fibrinogen, fibronectin and IgG was similar.

20 Inflammatory reaction in soft tissue.

The total number of cells in the exudates and associated with the surfaces of the machined, electropolished and electropolished plus anodized discs after different times of implantation are shown in Figs.3 and 4, respectively. The number of cells decreased with increasing observation periods at all implant types. No major differences in absolute total cell numbers were detected between the surfaces. Machined titanium pre-incubated in saline was one major exception revealing the highest cell numbers among all samples.

With one major exception, mononuclear cells (monocytes/macrophages, lymphocytes) were predominant in

the exudates around the implants at all time periods (1 d: machined Ti 33 % (HBSS) and 33 % (saline), electropolished 47 % (HBSS) and 50 % (saline, electropolished plus anodized (47 % (HBSS) and 55 % (saline; 3 d: machined Ti 81 % (saline), electropolished 87 % (saline), electropolished plus anodized 82 % (saline); 7 d: machined Ti 89 % (saline), electropolished 100 % (saline), electropolished plus anodized 94 % (saline). In contrast to the other implants, machined titanium had a markedly lower proportion of mononuclear cells after 1 d, and a correspondingly higher proportion of PMN. This discrepancy was not observed at other time points. No difference in the proportion of cells in the exudate was observed between implants which had been incubated in HBSS or saline.

15 Morphology and morphometry

Light microscopic observation

Paper I

After 7 weeks, immature bone with a woven character filled the cortical threads around all implants. At this time period, the merely electropolished implants had less endosteal intramedullary downgrowth of the bone than the machined and the electropolished plus anodized (180 nm thick oxide) implants. The electropolished plus anodized implants had the highest bone contact, 50% versus 20%, for the merely electropolished. After 12 weeks, the general organization of the bone around the implants was the same as that observed after 7 weeks. Only a small increase of the bone contact between 7 and 12 weeks were found for the electropolished plus anodized implants, however, for the two electropolished samples with a thin oxide the increased bone contact had reached the same level as the electropolished sample with thick oxide.

Papers II, IV

After 1 week the cortical bone was in general in close contact with the machined and machined/anodized implant types. Both the electropolished implant types had lower values for bone-implant contact at this time period (< 5%).

At 3 weeks newly formed bone from the endosteum reached the implant and filled the threads which were initially protruding into the marrow cavity. No quantitative differences were detected between the groups.

At 6 weeks, the electropolished implant had a lower bone contact than the electropolished plus anodized implant as well as the machined implants Fig.5. The electropolished implants also showed the lowest amount of bone within the threads. The two types of machined implants were surrounded by wider bone collar than the electropolished implants. In general, the bone was to a large extent in direct contact with the implant surfaces.

After 1 year, almost all threads were filled with lamellar bone and the implant surfaces were in close contact with the surrounding bone (60-70%) (Fig.6). The bone response to the different implant types were similar. The bone response around the electropolished implant group was equivalent with the other groups after one year.

Paper V

After 1 week the cortical bone was often in close contact with the implants although no new bone formation was seen at the cut edge of the cortex. No quantitative differences were seen between the groups.

At 3 weeks newly formed bone from the endosteum reached the implant and filled the threads which were initially occupied with marrow tissue. Marked signs of resorption and osteoid characterized the surface of the cortical and

trabecular bone facing the implant surface. Also at this time point no differences in bone contact or bone area were detected between the groups.

At 6 weeks, no qualitative or quantitative differences were found between the groups. The bone was to a large extent in direct contact with the implant surfaces and these observations were similar to those detected in paper II.

Ultrastructural observations

Paper III

10 A generally low degree of mineralization was found around the electropolished implants and together with the smooth fracture outline the production of ultrathin sections as well as the interpretation of the interface was made easier. There was constantly a layer of amorphous material
15 between the mineralized bone and the implant surface (0.2 μm wide). The electropolished plus anodized implants (thick oxide) were more difficult to examine (similar for the machined implants) since a separation of the implant from the plastic embedded tissue often resulted in disruption of
20 the interface tissue. The bone around the electropolished plus anodized implants had in general a much higher content of bone mineral than the merely electropolished implants. An amorphous layer was also found around these implants, generally somewhat thicker than for the merely
25 electropolished implants. The presence of a lamina limitans forming the border of the mineralized bone towards the implant was usually found around the electropolished plus anodized implants with thick oxide.

DISCUSSION

30 The relative importance of different surface properties for the biological performance of implanted biomaterials is largely unknown. The strategy chosen in the work was to systematically change the surface properties of titanium

implants and then evaluate the biological response in an animal model.

The surface chemistry, topography and microstructure of titanium surfaces have been varied in a well controlled manner in this thesis. There are several ways to modify the different properties although keeping all the parameters controlled is difficult.

Biocompatibility and modified titanium surfaces

Implantation of a non-biological material in biological surroundings leads to a time- and partly material-dependent sequence of inflammatory and reparative processes, although, as reviewed in the Introduction, the various material-related factors that influence these responses are not fully understood it is evident that protein adsorption and cellular adhesion to material surfaces are essential components of the tissue responses. In previous studies in this laboratory (reviewed in the Introduction), the soft tissue reactions around machined titanium surfaces have been characterized, including the cellular distribution and structure of the titanium-metal interface in experimental and human applications.

In experimental studies *in vivo* and in different *in vitro* models, the surface wettability, chemical composition, pattern of protein adsorption and the influence of exogenous stimuli have been found to influence the inflammatory cell recruitment, distribution and secretory response. Further, on the background of an early (and transient) distribution of mononuclear and multinuclear cells on the machined titanium surface during the inflammatory events which precede bone formation in the interface (Sennerby et al., 1993a; Sennerby et al., 1993b) studies on protein adsorption and cellular recruitment and adhesion to surface-modified titanium implants were

initiated.

The observation from the present experiment on *in vitro* plasma protein adsorption and cellular recruitment and adhesion in soft tissues of the rat indicate that no major differences were observed at a few selected time points, irrespective of the different surface properties exhibited by the machined, electropolished and electropolished titanium discs. We have no explanation for the relatively higher cell numbers on machined titanium after 1 day. In agreement with other recent observations (Thomsen et al., *in manuscript*), the machined titanium samples were associated with both a relatively greater influx and association of cells to the surfaces after 1 day than the other materials. Further, our data indicate that this inflammatory response is higher if implants are pre-incubated in saline than HBSS (with calcium). Moreover, the inflammatory exudate associated with machined implants was associated with a higher proportion of PMN. Interestingly, gross inflammatory cells in the exudate from methyated gold, was associated with a relatively greater PMN predominance after 1 day (Lindblad et al., 1997).

The present result together with previous experimental and clinical studies using machine implants in soft tissues, provide an indication that also the electropolished and electropolished plus anodized implants belong to a group of materials with soft tissue biocompatible properties.

The osseointegration process

The osseointegration process and modified titanium surfaces

The systematic approach in papers I-V was undertaken with the purpose to evaluate if and how variations of the metal implant surface properties could induce a variation of the bone reactions, as evaluated by light microscopic

morphometry and ultrastructural analysis. Thus, the thickness, morphology, topography and chemical composition of the surface layer could be more or less intentionally varied. Since the machined titanium constituted the implant on which surface modifications were made and, further, since a volume of scientific data exists on the material, biological and clinical properties of machined titanium implants, these implants were always included as a reference in the separate experiments.

10 In spite of the widespread use of machined titanium implants in bone, the mechanisms for achieving osseointegration has been less well understood. Previous experimental studies using the same experimental model as in this thesis (Sennerby et al., 1993a; Sennerby et al., 15 1993b) that the implant surface did not serve as an attachment for osteoblasts and no evidence was obtained indicating that mineralization was initiated on the surface: instead bone formation was observed after 3 days in the endosteum from which bone trabeculae projected towards the implant, and after 7 days as solitary islands within the threads. In both locations mineralization occurred by deposition of mineral in the collagenous matrix. Thus, the bone was growing towards the implant surface and the collagenous matrix of the interface zone 20 was the last part of the surrounding bone to become mineralized. After longer time periods, observations from animal experiments and human retrieval studies (reviewed in the Introduction) indicate that osseointegration of non-functionally and functionally loaded machined, threaded 25 titanium implants is characterized morphologically by a high amount of remodeled bone within the threads, a high bone-implant contact and a separation of mineralized bone from the implant surface by a thin zone of amorphous material.

30

In summary, the surface modified titanium implants evaluated in the present study (paper I-V) were found to essentially share biological properties with machined titanium: early bone formation proceeded towards the
5 implant surface and at later time periods all implants were osseointegrated.

A major exception was the relatively low bone contact observed with electropolished implants in the early phase (papers I-II). A possible explanation for this observation
10 could be the existence of an initial, larger gap between the electropolished implants and the surrounding tissue (due to the removal of less than $100\text{ }\mu\text{m}$ ($\sim 50\text{ }\mu\text{m}$) of the implant surface during the electrochemical process). However, the lower rate of bone formation around merely
15 electropolished samples after 6 weeks in comparison with the electropolished plus anodized samples can not be explained by the difference in possible initial gap between the implant surface and the tissue. It is suggested that the combination of a heterogeneous submicron roughness
20 (smooth/rough; 75%/25%), increased oxide thickness (180 nm) and thereby an increased crystallinity on the electropolished plus anodized surface are advantageous properties associated with the electropolished plus anodized implants. This combination of properties has not
25 been utilized previously as part of an implant element but reports in the literature indicate that for instance the degree of crystallinity may (as a single property) affect cell behaviour.

In studies in vitro an increased crystallinity (while
30 keeping oxide thickness and roughness parameters constant) was found to influence the phenotypic expression of osteoblasts (Boyan et al., 1995). In vitro studies have also shown that the roughness of the culture substratum influences osteoblast-like cell proliferation,

differentiation and matrix production (Martin et al., 1995). Further, cells at different stages of differentiation *in vitro* respond differently to the same surface (Boyan et al., 1995; Schwartz et al., 1996).

5 Therefore, if extrapolating to *in vivo* conditions it is possible that the titanium-bone interactions could be different at early and late time periods depending on time-dependent changes in the interface of the types of cells present and their maturity stage.

10 Although conflicting data exist in the literature, previous studies *in vivo* indicate that an increased surface roughness (on the $>1\ \mu\text{m}$ level) may promote bone adaptation to titanium surfaces (Buser et al., 1991; Goldberg et al., 1995; Gotfredsen et al., 1995). It is therefore

15 interesting, on the basis of the present one year data (paper IV) that firstly, all surfaces (machined, machined plus anodized, electropolished, electropolished plus anodized), being relatively smooth compared to sandblasted or plasma sprayed surfaces exhibited a high degree of bone-

20 to-implant contact and a high proportion of bone within threads, and secondly, that the morphometric values were equal to or higher than the values given for relatively rougher surfaces in another study using the same experimental model (Wennerberg, 1996). We have no clear

25 explanation for these findings. One possibility is that the smooth electropolished surface had acquired a thicker oxide and thereby a changed topography during the longer implantation period (1 year). Some evidence that such processes may be operative is the finding, in human

30 retrieval studies, that the thickness of the oxide had increased with time (Lausmaa, 1988; McQueen et al., 1982; Sundgren et al., 1986). Another possibility is that the rate of bone formation and mineralization around the machined and surface modified titanium implants was

influenced by ion release. Titanium ions (Ti^{4+}) have a dose related inhibitory effect on calcification *in vitro* (Blumenthal and Cosma 1989). The ion release rates *in vitro* from titanium materials decay with time due to self
5 passivation (Healey and Ducheyne, 1992a; Healey and Ducheyne, 1992b). Therefore, due to a relatively thinner oxide we cannot exclude that the electropolished implants are associated with a higher ion release.

Another hypothesis is that the titanium surface oxide,
10 through its ability to bind calcium could favour mineralization, which in turn might be beneficial for bone formation (Hanawa, 1990). However, it has not been shown that this would have an effect on osteoblast adhesion, proliferation, secretion of extracellular matrix and
15 mineralization of the titanium-interface zone. Previous *in vivo* data (Sennerby et al., 1993a; Sennerby et al., 1993b) and the present data (papers I-V) do not indicate that this is valid under the "*in vivo*" conditions.

However, the anionic TiO_2 attracts cations, like for
20 instance calcium, and it has been suggested that calcium binding may be one mechanism by which proteins adsorb to TiO_2 (similar to hydroxyapatite) (Ellingsen, 1991). Pre-treatment of TiO_2 by adsorption of lanthanum ions causes an increased adsorption of proteins, coinciding with an
25 inferior bone response in rats and rabbits (Ellingsen and Pinholt, 1995). In addition, pre-treatment of titanium implants with fluoride ions has been shown to increase push-out values (Ellingsen, 1995). Thus, a chemical
30 modification of the titanium surface may influence the bone tissue response, possibly by the adsorption of proteins to the surface. This hypothesis is mainly supported by *in vitro* studies which have shown that chondroitin-4-sulphate is bound to TiO_2 in the presence of calcium ions. Thus, tentatively in the amorphous zone, calcium bound to TiO_2

could promote the adsorption of sulphated glycosaminoglycans (Collis and Embury, 1992).

Taken together, chemical modifications of the titanium oxide surface have been found to affect the adsorption of macromolecules on the surface, and the tissue response. There are yet no evidence, however, that the positive effects on the bone response are due to a process of bone formation and mineralization which is directed outwards from the TiO_2 -surface. A future approach with the purpose to further modulate the bone response may be to selectively adsorb/incorporate molecules to the surface which could influence bone precursor cells/osteoblasts and enhance mineralization. However, since the interactions between proteins, cells and such a chemically treated surface may be influenced not only by the chemical properties of the surface but also by the surface submicron roughness, an optimization of both chemical and surface roughness parameters have to be considered when new implants are designed. The present invention is not limited to be used as an implant surface as such but may be utilized as a substrata for such purposes.

On the basis of available literature (reviewed above) and knowledge it may be concluded that the integration of titanium implants and bone and the maintenance of this integration are prerequisites for the clinically documented long-term function and high success rates. However, the kinetics of the process of osseointegration described above implies that the early phase of healing prior to adequate stability might be particularly crucial in situations with an inferior bone quality and other negative host factors. Experimental studies on threaded titanium implants in more or less compromised local implant beds (previous irradiation of tissues or local inflammation and osteopenia) support this assumption (Sennerby and Thomsen

1993; Öhrnell et al., 1997). Further, studies in patients with rheumatoid arthritis have shown a reduced mechanical capacity (decrease in torsional strength) of the bone-titanium unit in comparison with patients with
5 osteoarthritis (Brånemark, 1996).

On the basis of the present results during the early phase of healing it is suggested that machined and electropolished c.p. titanium implants with polycrystalline, thick oxides and a microporous roughness on
10 the submicron level may be interesting materials to be evaluated under clinical conditions. However, it is apparent that also an adequate remodelling of bone around the implants is required in order to promote a long-term stability. It is therefore of interest that in our long-
15 term (1 year) study (paper IV) the experimental results showed that all four types of threaded, titanium implants, irrespective of surface modification (machined, machined and anodized, electropolished, electropolished and anodized), had a high degree of bone-to-implant contact and
20 a high proportion of mature, lamellar bone within threads. Thus, implants with a similar chemical composition but with marked differences in oxide thickness, surface topography and roughness, became equally well osseointegrated under long-term experimental conditions.

25 The examples given above have shown that it is possible to produce titanium implants with surface modifications which vary with respect to oxide thickness, composition, topography, roughness and microstructure. On the basis of results in thesis by Larsson (1997) it may be summarized
30 that

* in comparison with the merely electropolished implants (which had a very smooth surface with a thin, non crystalline oxid) and machined implants, the implants which were surface modified with anodization acquired a thicker

oxid (180-200 nm), increased crystallinity and increased roughness on the submicrometer scale.

* A high degree of bone surrounding, and in contact with the implant, was found for all titanium implants, irrespective of surface modification. Taken together, the light microscopic, morphometric and ultrastructural observations indicate that the process of osseointegration is basically similar for machined and surface modified titanium implants.

10 * The results of the biological experiment show that a combination of increased oxide thickness, oxide crystallinity and roughness on the submicrometer scale are advantageous properties for the early bone response, particularly in comparison with thin, smooth non-crystalline oxide surfaces.

* A high degree of bone-to-implant contact and a high proportion of lamellar bone within the threads of the implants are observed after one year, irrespective of surface modification (machined, machined plus anodized, electropolished and electropolished plus anodized). The latter results indicate that the combination of surface properties (increased oxide thickness, increased crystallinity and roughness on the submicrometer scale) of anodized implants have equal long-term biological properties in bone as the clinically used machined titanium implants.

Taken together, our observations indicate that a titanium surface with a combination of surface properties (increased oxide thickness, increased crystallinity and roughness on the submicrometer scale), acquired in the present experiments by anodization, constitute an important element of implanted device.

Table I. Summary of the results from surface characterization of the implants.

Preparation (paper)	Sterilization	Contamination at%	Oxide/nitride thickness (nm)	Rrms, (nm)	Adiff, %	Microstructure and oxide crystallinity
Machined (I, III)	steam sterilized	45-80 at% C (Ca, S, Si, P, Cl and Na)	4	29	-	Plastically deformed, amorphous metal surface, non-crystalline oxide
Electropolished (I, III)	steam sterilized	55-90 at% C (Ca, S, Si, P, Cl, and Na)	4-5	2.7	-	Polycrystalline metal surface, non- crystalline oxide
Electropolished+anodized, (I, III)	steam sterilized	55-70 at% C (Ca, S, Si, and Cl)	21	1.5	-	Polycrystalline metal surface, non- crystalline oxide
Electropolished+anodized, (I, III)	steam sterilized	34-40 at% C (Ca and Cl)	180	16	-	Polycrystalline metal surface. Partly crystalline oxide (anatase)
Machined (II, IV)	steam sterilized	34.4 at% C, 1.7 at% Cl, 3.5 at% Na, (Ca, S, P, Si, and F)	3-5	30.3	10.8	Plastically deformed, amorphous metal surface, non-crystalline oxide
Machined+anodized, (II, IV)	steam sterilized	33 at% C, 1.1 at% Na, (Ca, S, P, Cl, and Si)	180-200	40.8	18.0	Plastically deformed, amorphous metal surface, non-crystalline oxide
Electropolished (II, IV)	steam sterilized	26.9 at% C, (Ca, S, Cl and Na)	3-5	2.9	0.5	Polycrystalline metal surface, non- crystalline oxide
Electropolished+anodized, (II, IV)	steam sterilized	25.2 at% C (S, Cl and Na)	180-200	32.3 2.7 (smooth) 116.7 (rough)	23.3 0.6 (smooth) 88.0 (rough)	Polycrystalline metal surface Partly crystalline oxide
Machined (V)	γ -irradiated	23 at% C (Ca, Si, S and Cl)	≈ 3	26.3	13.1	Plastically deformed, amorphous metal surface, non-crystalline oxide
Glow discharge cleaned and thermally oxidized (V)	γ -irradiated	12 at% C (S)	≈ 2	10.2	0.78	Polycrystalline metal surface, non- crystalline oxide
Glow discharge cleaned and nitrided (V)	γ -irradiated	10 at% O and C (Si)	TiN= 3	25.2	8.63	Polycrystalline metal surface, non- crystalline oxide
Hydrogen peroxide treated (V)	-	12 at% C (Ba, Cl and Zn)	7	25.6	20.5	Plastically deformed, amorphous metal surface, Non-crystalline oxide

Table II. The mean value for the three measurements (drops on one disc) are presented. The value for each drop (mean for right and left side of the drop) is presented within parentheses.

Preparation	H ₂ O advancing (contact angles)	H ₂ O receding (contact angles)	CH ₂ I ₂ advancing (contact angles)	CH ₂ I ₂ receding (contact angles)
Machined	41.2 (37, 44.5, 42)	- (18, <10, 13)	47 (43, 46, 53)	42 (39.5, 40.5, 45.5)
Electropolished	39.5 (38.5, 37.5, 42.5)	- (12.5, 14.5, <10)	35 (37.5, 32, 36.5)	32 (31, 30.5, 33.5)
Electropolished and anodized	22 (23, 22, 20.5)	<10 (<10, <10, <10)	42.5 (45.5, 38.5, 43.5)	32 (35, 32.5, 29)

5 Table III: The surface energy for the different samples.

Preparation	Surface energy dyne/cm	Polar component	Dispersion component
Machined	58.1	33.6	24.4
Electropolished	61.3	32.2	29.1
Electropolished and anodized	68.6	42.8	25.8

CLAIMS

1. An implant element for permanent anchorage in bone tissue in which at least the surface intended to face the tissue in the implantation region is made of titanium with a titanium oxide surface characterized in that the implant surface is modified by anodization to acquire an oxide thickness of approximately 10-200 nm, an increased surface oxide crystallinity and roughness on the submicrometer scale in order to provide a high degree of bone-to-implant contact.
2. An implant element according to claim 1 characterized in that the degree of surface oxide crystallinity is increased compared to a machined titanium surface.
3. An implant element according to claim 1 characterized in that the anodized surface is a heterogeneous surface with irregularly distributed smooth and rough areas.
4. An implant element according to claim 3 characterized in that the rough areas are 10-100 μm large.
5. An implant element according to claim 3 characterized in that the rough areas of the surface have a roughness in the range of 10 nm to a few μm .
6. An implant element according to claim 3 characterized in that the ratio between the smooth and rough areas are larger than 1 and preferably about 3.



Fig. 1 a



Fig. 1 b




Fig. 1 c




Fig. 1 d




Fig. 2 a




Fig. 2 b




Fig. 2 c

5/6




Fig. 3






Fig. 4

6/6



INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 98/00891

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: A61C 8/00, A61L 27/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: A61C, A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0676179 A2 (FRIATEC AG KERAMIK- UND KUNSTSTOFFWERKE), 11 October 1995 (11.10.95), claims 1-4 --	1-6
X	US 5354390 A (KÁROLY HASZMANN ET AL), 11 October 1994 (11.10.94), column 2, line 21 - column 3, line 13 --	1-6
X	STN International, File CA, Chemical Abstracts, volume 99, no. 11, 12 September 1983, (Columbus Ohio, US), McQueen, D. et al: "Augar electron spectroscopic studies of titanium implants", abstract no. 86052, & Biomater. (1982), 4 (Clin. Appl. Biomater.), 179-85 --	1-6

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"I" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

19 August 1998

Date of mailing of the international search report

24 -08- 1998

Name and mailing address of the ISA:

Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Jack Hedlund
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 98/00891

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>STN International, File CA, Chemical Abstracts, volume 122, no. 22, 29 May 1995, (Columbus Ohio, US), Ishizawa, Hitoshi, "Implant for artificial dental roots, artificial bones, artificial joints, and bone fillers and its manufacture", abstract no. 274159, & JP,A2,07031627, 950203, Heisei</p> <p>-- -----</p>	1-6

INTERNATIONAL SEARCH REPORT
Information on patent family members

27/07/98

International application No.
PCT/SE 98/00891

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0676179 A2	11/10/95	DE 4407993 A	21/09/95
US 5354390 A	11/10/94	DE 4311772 A	14/10/93
		FR 2689911 A,B	15/10/93
		HU 213001 B	28/01/97

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record.

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☒ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)